


THE INFORMATION CONTAINED IN THIS DRAWING IS THE SOLE PROPERTY OF VTE INCORPORATED. ANY REPRODUCTION IN PART OR WHOLE WITHOUT THE WRITTEN PERMISSION OF VTE INCORPORATED IS PROHIBITED. VTE MAKES NO WARRANTY, EXPRESSED OR IMPLIED, AS TO THE SUITABILITY OF A PRODUCT FOR ANY INTENDED USE. THE CUSTOMER SHALL BEAR THE SOLE RESPONSIBILITY OF DETERMINING THE SUITABILITY OF ANY VTE PRODUCT FOR ITS END USE.

| LTR. | REVISIONS | DATE | INT. |
|------|-----------|------|------|
| | | | |

PREFERRED VENDOR:

NEXED

| | |
|-----------------------------------|-----------------------------------|
| MATERIAL PART NO: | 1103640115 |
| MATERIAL: | SANTOPRENE 201-64 |
| VENDOR PART NO: | TPE AES 201-64 NATURAL SANTOPRENE |
| SPECIFIC GRAVITY: | 0.970 |
| HARDNESS 15 SEC: | 69 |
| HARDNESS SCALE: | A |
| TENSILE STRENGTH, PSI: | 1020 |
| ELONGATION, %: | 450 |
| TEAR STRENGTH, PPI: | 131 |
| FLAME CLASS UL: | HB |
| BRITTLINESS TEMP., DEGREES F [C]: | -76 [-60] |
| MELT TEMP., DEGREES F [C]: | 380-450 [193-232] |
| DIELECTRIC STRENGTH, V/MIL: | 750 |

| | | | |
|---|--|---|---------------|
|  | | VTE Incorporated 5437 Robinson Road, P.O. Box 790 Pellston, Michigan 49769 Telephone: 1-800-527-9256, 231-539-8000 FAX: 231-539-0914 | |
| | | REF: | DATE: 21FEB17 |
| | | CHK'D BY: RAS | |
| TITLE: SANTOPRENE MATERIAL INFORMATION | | | |
| MATERIAL: SANTOPRENE | | PART NO. | |
| COLOR: NATURAL | | 1103640115 | |
| | | DRG CLASS | |