

THE INFORMATION CONTAINED IN THIS DRAWING IS THE SOLE PROPERTY OF VTE INCORPORATED. ANY REPRODUCTION IN PART OR WHOLE WITHOUT THE WRITTEN PERMISSION OF VTE INCORPORATED IS PROHIBITED. VTE MAKES NO WARRANTY, EXPRESSED OR IMPLIED, AS TO THE SUITABILITY OF A PRODUCT FOR ANY INTENDED USE. THE CUSTOMER SHALL BEAR THE SOLE RESPONSIBILITY OF DETERMINING THE SUITABILITY OF ANY VTE PRODUCT FOR ITS END USE.


LTR.	REVISIONS	DATE	INT.

ASSEMBLY CONSISTS OF:  
96%

MATERIAL PART NO: 1103640114  
 MATERIAL: SANTOPRENE 201-64  
 VENDOR PART NO: 201-64 NATURAL  
 SPECIFIC GRAVITY: 0.970  
 HARDNESS 15 SEC: 69  
 HARDNESS SCALE: A  
 TENSILE STRENGTH, PSI: 1020  
 ELONGATION, %: 450  
 TEAR STRENGTH, PPI: 131  
 FLAME CLASS UL: HB  
 BRITTLENESS TEMP., DEGREES C: -76 [-60]  
 MELT TEMP., DEGREES F: 380-450 [193-232]  
 DIELECTRIC STRENGTH, V/MIL: 750

4%

COLORANT PART NO: 1214030002  
 MATERIAL: RED COLORANT  
 MATERIAL PART NO: GE33631300  
 COLORANT FOR: SANTOPRENE  
 MATERIAL NAME: SPR SANTO 201-64 025.000:1

		<b>VTE Incorporated</b> 5437 Robinson Road, P.O. Box 790 Pellston, Michigan 49769 Telephone: 1-800-527-9256, 231-539-8000 FAX: 231-539-0914	
		REF:	DATE: 21FEB17
		CHK'D BY: RAS	
TITLE: MATERIAL ASSEMBLY INFORMATION			
MATERIAL: RED MATERIAL		PART NO.	
COLOR: RED	DRG CLASS	7203640102	